



Technical Data Sheet

Product : CK 175

Fiber	Warp	Toray 3K 200 tex Kevlar 127 tex (2:1)
	Weft	Toray 3K 200 tex Kevlar 127 tex (2:1)
Area weight	175 g/m ² ± 3%	
Binding	Plain 1/1	
Width	100, 120 cm	
Sett of (per 1 cm)	Warp	5
	Weft	5
Compatibility	Epoxy resin	
Standard packing	100 m	

ISO 9001 : 2015
ISO 14001 : 2015



Kordcarbon a.s., 696 74 Velká nad Veličkou 890, Czech Republic
email : info@kordcarbon.com, www.kordcarbon.com