



Technical Data Sheet

Product : CCT 200

Fiber	Warp	Tenax™-E HTS40 E13 3K
	Weft	Tenax™-E HTS40 E13 3K
Areal weight	200 g/m ² ± 3%	
Weave	Plain 1/1, Twill 2/2	
Width	100 cm, 125 cm, on demand	
Thread count (1cm)	Warp	5
	Weft	5
Sizing	Epoxy, phenolic, polyester, vinyl ester	
Standard length of roll	100 lm, 200 lm on demand	

ISO 9001 : 2015
ISO 14001 : 2015



Kordcarbon, a.s., Úprkova 683, 696 62 Strážnice, Czech Republic

email : info@kordcarbon.com, www.kordcarbon.com