



Technical Data Sheet

Product : CK 164

Fiber	Warp	T3003 3K 40B Taparan 1100dtex/667F (2:1)
	Weft	T3003 3K 40B Taparan 1100dtex/667F (1:2)
Areal weight	164 g/m ² ± 3%	
Weave	Plain	
Width	85, 100, 120 cm, on demand	
Thread count (1cm)	Warp	5
	Weft	5
Sizing	Epoxy, phenolic, polyester, vinyl ester	
Standard length of roll	100 lm, 200 lm	

ISO 9001 : 2015
ISO 14001 : 2015



Kordcarbon, a.s., Úprkova 683, 696 62 Strážnice, Czech Republic

email : info@kordcarbon.com, www.kordcarbon.com