



## Technical Data Sheet

**Product : CK 175**

Fiber	Warp	T3003 3K 40B Taparan 1100dtex/667F (2:1)
	Weft	T3003 3K 40B Taparan 1100dtex/667F (2:1)
Areal weight	175 g/m <sup>2</sup> ± 3%	
Weave	Plain	
Width	100, 120 cm, on demand	
Thread count (1cm)	Warp	5
	Weft	5
Sizing	Epoxy, phenolic, polyester, vinyl ester	
Standard length of roll	100 lm, 200 lm	

ISO 9001 : 2015  
ISO 14001 : 2015



Kordcarbon, a.s., Úprkova 683, 696 62 Strážnice, Czech Republic

email : [info@kordcarbon.com](mailto:info@kordcarbon.com), [www.kordcarbon.com](http://www.kordcarbon.com)